

Technical Data TURBO POWER

Types of leather: Pigmented, Semi-Aniline, Aniline, Nubuk	Max. thickness: 1,3 MM
Turbo Power type of leather: Pigmented	Min. thickness: 1,1 MM
Product characteristics: Leather for automotive.	Average size of the hide: 4,0 – 5,0 sq.m.
Country of origin: Italy	Minimum size of the hide: 3,5 sq.m.
Crust color: match leather color	Stamp: no stamps
Raw skin region of origin: Europe	Production time: 45 days

Test Name	Normative	Test result
Abrasion	ASTM D 4157	200000 to 400000 Double Rubs
Abrasion	BS 2543	100000 Double Abrasion (Martindale)
Tensile strength	ISO 3376	
Tear strength	ISO 3377/1-2	Sec 14
Crocking	AATCC 8	Class 5 Wet & Dry
Light	AATCC 16-3	Class 4-5
Gas	AATCC 23	Class 4,5
Ozone	AATCC 109	Class 5
Fire resistance Rating	FMVSS 302	pass
	CA 117 E	Class 1
	UFAC	Class 1
	NFPA 250	Class 1
	ASTM E 84 (Adhered)	Class A

LEATHER CARE



Avoid direct sunlight.



Avoid hot temperature.



Wipe regularly with a soft dry cloth.

CLEANING AND STAIN REMOVAL



Any stains can be removed using a damp cloth with mild soap and water. Suggested soap with pH = 7.



Gently wipe the stain from the center to the edge.



Wipe gently until the stains are removed. Avoid rubbing.